

ALF 4047

Standards

AWS 5.8	Al-Si 12
EN ISO 3677	B-AL88Si - 575/585
EN ISO 18273	Al 112
EN 1044	AL 104

Product Features and Advantages

Generally used for aluminium and aluminium alloys brazing. Prefably used for mass production for easy use due to containing flux.

Alüminyum Sert Lehim Alaşımaları - Sert Lehim Teli

Applications

It has wide range of use such as pipe connections, air conditioning and cooling, aluminium motor blocks, aluminium radiators and pipes.

Typical Physical Analysis of the Weld Metal

Working Temperature (°C)	Melting Temperature (°C)	Density (gr/cm ³)	Conductivity (Sm/mm ²)
590	575-590	2.65	21

Packaging Information

Product Code	Diameter x Length (mm)	Quantity per Box	Box Gross Weight (kg)	Boxes per Outer Box	Outer Box Gross Weight (kg)	Packaging Type
80414BKA04	2.00x500	1.00 KG	1.10	1	1.10	Carton Envelope