

BMT-250

SUBMERGED WELDING POWDER DRYER WITH DIGITAL THERMOSTAT

CAPACITY	125+125= 250 KG
HEIGHT	70 TABLE-138 CM
LENGTH- WIDTH	120-140 x 75 CM
TEMPERATURE	0-400 °C
ELECTRIC POWER	6000 W
ELECTRIC VOLTAGE	380 V
TOTAL CURRENT	15 A
WEIGHT	230 KG

The main operating principle is to get factory output arc welding powder in high temperatures for shocking process and to keep them in lower temperature for keeping them dry.

The factory output powders are kept at 300 °C for 2 hours in order to complete the shocking process and then, the thermostat shall be taken back to 130 °C and the flux shall be left for resting process.





OUR COMPANY HAS ISO 9001:2008
ISO 18001 OHSAS, CE CERTIFICATES.
IF DESIRE TO BE CERTIFIED TÜRK-AK TS-EN ISO-IEC 17025 CAN DEVICES ARE MADE CALIBRATION

